



















Technical Data Sheet

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Core Volume (%)	Units Per m ²	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) (MPa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	eFactor (mm/m)	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Metallix	Blackstone			NSW	230	110	76	DW1	3	<35	48.5	400	>10	<10	0.1-4.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	Dark
Metallix	Bronze			NSW	230	110	76	DW1	2.8	30-40	48.5	400	>10	<10	0.1-4.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	Dark
Metallix	Cherry Soda			NSW	230	110	76	DW1	3	<30	48.5	400	>10	<10	0.1-4.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	Dark
Metallix	Cuprum			NSW	230	110	76	DW1	2.8	30-40	48.5	400	>10	<10	0.1-4.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	Dark
Metallix	Gun Metal Blue			NSW	230	110	76	DW1	3	<38	48.5	400	>10	<10	0.1-4.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	Dark
Metallix	Lithium			NSW	230	110	76	DW1	2.8	<38	48.5	400	>10	<10	0.1 - 3.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	Dark
Metallix	Platinum			NSW	230	110	76	DW1	2.8	30-40	48.5	400	>10	<10	0.1-4.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	Medium
Metallix	Quartz			NSW	230	110	76	DW1	2.8	<38	48.5	400	>10	<10	0.1 - 3.0	<1.2	General Purpose	Nil to slight	Nil to slight	Dark
Metallix	Titanium			NSW	230	110	76	DW1	2.8	30-40	48.5	400	>10	<10	0.1-4.0	<1.2	Exposure Grade	Nil to slight	Nil to slight	Dark