





















18 Michigan Road
Kelso, NSW 2795

Phone 02 6332 2717
www.centralwestbricks.com

Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	Division	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Nelissen	Mechelen			Import	215	100	65	DW1	2.5	Solid	59	730	>5	<15	1.0-8.0	<1.0	Exposure Grade	Nil to Slight	Nil to Slight	TBA
Nelissen	Gent			Import	215	100	65	DW1	2.5	Solid	59	730	>5	<15	1.0-8.0	<1.0	Exposure Grade	Nil to Slight	Nil to Slight	TBA
Nelissen	Hasselt			Import	215	100	65	DW1	2.5	Solid	59	730	>5	<18	1.0-8.0	<1.0	General Purpose	Nil to Slight	Nil to Slight	TBA
Nelissen	Limburg			Import	215	100	65	DW1	2.5	Solid	59	730	>5	<18	1.0-8.0	<1.0	General Purpose	Nil to Slight	Nil to Slight	TBA
Nelissen	Charleroi			Import	215	100	65	DW1	2.5	Solid	59	730	>5	<18	1.0-8.0	<1.0	General Purpose	Nil to Slight	Nil to Slight	TBA
Nelissen	Bruges			Import	215	100	65	DW1	2.5	Solid	59	730	>5	<18	1.0-8.0	<1.0	General Purpose	Nil to Slight	Nil to Slight	TBA
Nelissen	Ostend			Import	215	100	65	DW1	2.5	Solid	59	730	>5	<18	1.0-8.0	<1.0	General Purpose	Nil to Slight	Nil to Slight	TBA
Nelissen	Tournai			Import	215	100	65	DW1	2.5	Solid	59	730	>5	<18	1.0-8.0	<1.0	General Purpose	Nil to Slight	Nil to Slight	TBA
Nelissen	Ypres			Import	215	100	65	DW1	2.5	Solid	59	730	>5	<18	1.0-8.0	<1.0	General Purpose	Nil to Slight	Nil to Slight	TBA