

**Product Details**

range name	TECHPAVE
finish	SMOOTH   HONED*   SHOT BLAST*
colours	CHARCOAL, ALMOND, NATURAL, TERRACOTTA
product code   description	TECHPAVE 80

**Properties and Specifications**

actual dimensions (length x width x height mm)	230 X 115 X 80MM
dimensional category	DPA2
average weight (KG)	4.3
durability class Salt resistant as per AS/NZS4456.10: 2003	General Purpose
number per sqm/lm	37.8
number per pallet	-
characteristic breaking load (kN)	10
mean cold water absorption (%)	-
mean abrasion resistance	7
slip resistance category	P5   very low risk, > 54 BPN
modulus of rupture (MPa)	4
	-

**Diagram**



18 Michigan Road  
Kelso, NSW 2795

**Phone 02 6332 2717**  
[www.centralwestbricks.com](http://www.centralwestbricks.com)

*Tested as per AS/NZS 4456: 2003 and 4586: 2013. \* Made to order and by request only*

*This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact UrbanStone for confirmation of product specification*

**Product Details**

range name	TECHPAVE
finish	SMOOTH   HONED*   SHOT BLAST*
colours	CHARCOAL, ALMOND, NATURAL, TERRACOTTA
product code   description	TECHPAVE 100

**Properties and Specifications**

actual dimensions (length x width x height mm)	200 X 110 X 100MM
dimensional category	DPA1
average weight (KG)	4.5
durability class Salt resistant as per AS/NZS4456.10: 2003	General Purpose
number per sqm/lm	45.5
number per pallet	-
characteristic breaking load (kN)	10
mean cold water absorption (%)	-
mean abrasion resistance (CM <sup>3</sup> )	7
slip resistance category	P5   very low risk, > 54 BPN
modulus of rupture (MPa)	4
	-

**Diagram**



18 Michigan Road  
Kelso, NSW 2795

**Phone 02 6332 2717**  
[www.centralwestbricks.com](http://www.centralwestbricks.com)

*Tested as per AS/NZS 4456: 2003 and 4586: 2013. \* Made to order and by request only*

*This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact UrbanStone for confirmation of product specification*