













Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorbance Rating
Stratos	Cloudy Sunset			NSW	230	110	76	DW1	2.8	<40	48.5	400	>15	<10	0.1-1.0	<1.0	Exposure Grade	Slight	Slight	TBA
Stratos	Coastal Storm			NSW	230	110	76	DW1	2.8	<40	48.5	400	>15	<10	0.1-1.0	<1.0	Exposure Grade	Slight	Slight	TBA
Stratos	Dark Cumulus			NSW	230	110	76	DW1	2.8	<40	48.5	400	>15	<10	0.1-1.0	<1.0	Exposure Grade	Slight	Slight	TBA
Stratos	Light Cirrus			NSW	230	110	76	DW1	2.8	<40	48.5	400	>15	<10	0.1-1.0	<1.0	Exposure Grade	Slight	Slight	TBA
Stratos	Morning Mist			NSW	230	110	76	DW1	2.8	<40	48.5	400	>15	<10	0.1-1.0	<1.0	Exposure Grade	Slight	Slight	TBA
Stratos	Winter Frost			NSW	230	110	76	DW1	2.8	<40	48.5	400	>15	<10	0.1-1.0	<1.0	Exposure Grade	Slight	Slight	TBA

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

November 2021