



18 Michigan Road
Kelso, NSW 2795
Phone 02 6332 2717
www.centralwestbricks.com



Range: Overland

Colour: Franklin Gordon Blend

SKU: 710910017320001236100

Technical Data

Length (mm)	230
Width (mm)	110
Height (mm)	76
Dimensional Category	DW1
Core Volume (%)	25
Units per Square Metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f'uc) MPa	>12
Maximum Cold Water Absorption (%)	12
Initial Rate of Absorption (IRA) (kg/m ² min)	0.5-2.5
Coefficient of Expansion e'Factor (mm/m)	1.0

Durability Class	Exposure Grade
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorption	0.79
LRV	7.7
Place of Manufacture	Victoria
Product Warranty	100 Years
Solar Absorption	0.79
Meter squared	48.5
Weight	3.2

A BRAND OF

BRICKWORKS



18 Michigan Road
Kelso, NSW 2795
Phone 02 6332 2717
www.centralwestbricks.com



Range: Overland

Colour: Tasman Blend

SKU: 710910017300001236100

Technical Data

Length (mm)	230
Width (mm)	110
Height (mm)	76
Dimensional Category	DW1
Core Volume (%)	25
Units per Square Metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f'uc) MPa	>12
Maximum Cold Water Absorption (%)	12
Initial Rate of Absorption (IRA) (kg/m ² min)	0.5-2.5
Coefficient of Expansion e'Factor (mm/m)	1.0

Durability Class	General Purpose
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorption	0.63
LRV	19.2
Place of Manufacture	Victoria
Product Warranty	100 Years
Solar Absorption	0.63
Meter squared	48.5
Weight	3.2

A BRAND OF

BRICKWORKS